PERSPEX® FROM LUCITE®

PERSPEX® XT EXTRUDED

Perspex® from Lucite® Technical Data Sheet

Table of Properties

Values quoted for the properties of Perspex® from Lucite® are the results of tests on representative samples and do not constitute specifications.

Property					IMPACT MODIFIED	
	Test Method	Units	0x00	IM50	IM60	
General Properties						
Relative Density	ISO 1183	-	1.19	1.17	1.16	
Rockwell Hardness	ISO 2039-2	M scale	101	65	45	
Water Absorption	ISO 62	%	0.2	0.3	0.3	
Flammability	DIN 4102	-	B2	B2	B2	
	UL94	-	НВ	НВ	НВ	
	BS 476 Part 7	Class	4	-	-	
	NFP 92-507		M4			
	ISO 11925-2	-	Е	-	-	
Mechanical Properties						
Tensile strength (5 mm/min)	ISO 527	MPa	70	68	50	
Elongation at Break (5 mm/min)	ISO 527	%	4	18	25	
Flexural Strength (2 mm/min)	ISO 178	MPa	107	90	70	
Flexural Modulus (2 mm/min)	ISO 178	MPa	3030	2500	2000	
Charpy Impact Strength (unnotched)	ISO 179 ISO 179	kJ.m ⁻² kJ.m ⁻²	10 -	50 5	65 7	
Izod Impact Strength	ISO 180/1A	kJ.m ⁻²	-	5	7	





Talk to us Tel: +44 (0)1254 874000 info@lucitesolutions.com www.lucitesolutions.com



Values quoted for the properties of Perspex® from Lucite® are the results of tests on representative samples and do not constitute specifications.

Property	Test Method	Units	0x00	IM50	IM60
Thermal Properties					
Vicat Softening Point	ISO 306 A	°C	> 105	> 105	> 105
Coefficient of Thermal Expansion	ASTM D696	x 10 ⁻⁵ . K ⁻¹	7.8	-	-
Optical Properties					
Light Transmission	ASTM D1003	% (3 mm)	> 92	90	89
Refractive Index	ISO 489 A	-	1.49	-	-
Electrical Properties					
Surface Resistivity	IEC 93	Ω .m $^{-2}$	>1014	-	-
Electrical Strength	IEC 243	kV.mm ⁻¹	-	-	-

The information is given in good faith and is based on our general experience, but because of the many particular factors which are outside our knowledge and control that affect the use of products, no warranty is given or is to be implied. Freedom from patent rights must not be assumed.